



SISTEMI INNOVATIVI

REV. 191015

LIBECCIO FINISH

Premixed superfine mineral tonachino based on highly breathable marble powder for interiors

CHARACTERISTICS

FINITURA **LIBECCIO** is a premixed mineral plaster, white in colour, superfine, highly breathable, of great value and with a smooth effect, of superior quality, based on marble dust, hydraulic binders and specific additives, suitable for interiors.

It is used on new supports, on walls and ceilings, before being painted. It also has extremely easy to apply.

If you want, you can paint it or leave it in its natural state with a smooth marble effect.

FIELDS OF USE

The **LIBECCIO FINISH** is used indoors as a high-quality smooth undercoat/finish on new, smooth or rough surfaces, on walls and ceilings, before being painted with water-based paints or products from the Contrasti range. It is ideal on our **TONACHINO LIBECCIO**, **TONACHINO LIBECCIO EXTRA**, **TONACHINO LIBECCIO PLUS**, **RASOX PLUS F**, etc.

PREPARATION OF THE SUPPORT

Make sure the surface is clean and free from dust, oil, grease, paint, flaking parts and layers of separating substances. Any burrs on the surface must be removed and leveled before applying the **FINITURA LIBECCIO**.

Moisten the substrate before application only if necessary.

HOW TO USE

For mixing with low speed electric stirrer number of revolutions, add approximately 9.5 litres of clean water to each 25 kg bag. The mixing time must not exceed 5 minutes.

Let the product rest for about 10 minutes before of use. Then proceed with a stainless steel spatula with two hands: the first to smooth and, after about 30-60 minutes, apply the second, smoothing until obtaining a smooth and homogeneous surface.

As soon as the **LIBECCIO FINISH** is dry, after applying the relevant primers, proceed with painting the surfaces if desired.

WARNINGS

- The **LIBECCIO FINISH** must be used as is, without the addition of foreign materials.

- The working time varies according to the temperature and in any case the **FINITURA LIBECCIO** must be applied within 2 hours of mixing. • It is recommended to use a specialized product. • Do not apply at temperatures

below 5°C and above 35°C. • Do not apply labor with relative humidity below 100°C.

35% and above 85%.

- Avoid application in the presence of strong winds and beating sun.

BOLLETTINO TECNICO



REV. 191015

SPECIFICATION ITEM

Application, for internal surfaces, of premixed superfine mineral plaster in white colour, highly breathable, of great value and with a smooth effect, of superior quality, based on marble dust, hydraulic binders and specific additives, suitable for new supports, both smooth and rough, on walls and ceilings, ideal on **TONACHINO LIBECCIO BUFFA, TONACHINO LIBECCIO EXTRA BUFFA, TONACHINO LIBECCIO PLUS BUFFA, RASOX PLUS F BUFFA**, etc. to be applied in two coats with a smooth stainless steel spatula, with an average consumption of 1.2 / 1.6 kg per m² for two coats, type **FINITURA LIBECCIO BUFFA**.

TECHNICAL DATA

DILUTION	38% approx.
I WAIT	dust
COMPOSITION	- marble powder - hydraulic binders - specific additives 6 ~
DRYING	8 hours approximately at 23° C
SANDING INTERVAL	minimum 24 hours
OVERPAINTABILITY	24 - 48 ore
TRIP	1.2 / 1.6 kg per m ² for two coats
COLOR	white
PACKAGES	25 kg bags 12
STORAGE	months if stored in intact packages, away from heat, frost and humidity
TOXICITY	See safety data sheet

These times, calculated at 22°C, are lengthened by low temperatures and reduced by heat.

ATTENTION

The information, instructions and indications above are the result of our best technical and applicative knowledge; nevertheless, they are to be considered purely indicative. Therefore, it is the user's responsibility to verify, assuming full responsibility, the compatibility of the products with the intended use, since we cannot intervene directly on the conditions of the construction sites and the methods of carrying out the works. In this regard, a preliminary test is recommended in order to verify the suitability of the product for the intended use.